

# Test Report Date: MAR.20, 2017 Page 1 of 6

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: PVC COATED MESH

**Color**: WHITE

**Density**: 260G/M<sup>2</sup>

### **Test Requested:**

To determine the flammability (building materials class B1) in accordance with DIN 4102-1 (May 1998) Fire behaviour of building materials and elements Part 1: Classification of building materials, Requirements and testing

Test Results: -- See attached sheet --

Classification: The tested sample meets class B1 building materials requirements of DIN 4102-1 (May

1998).

#### **Test Period:**

Sample Receiving Date : MAR.01, 2017

Test Performing Date : MAR.01, 2017 TO MAR.16, 2017

中国·浙江·安吉县阳光工业园二区阳光大道301号

Signed for and on behalf of SGS-CSTC Co., Ltd. Anji Branch

Allen Zou

Technical Manager



邮编:313300 t (86-572) 5018625 f (86-572) 5018629 e sgs.china@sgs.com



## Test Report Date: MAR.20, 2017 Page 2 of 6

#### I. Test conducted

This test was conducted as per DIN 4102-15:1990 DIN 4102-16:1998 and DIN 4102-1:1998 Clause 6.2, and Classification in according to DIN 4102-1 (May 1998) Clause 6.1-Class B1 materials.

### II. Sample details

General description / Color	PVC COATED MESH / White
Density	About 260 g/m <sup>2</sup>
Size of sample	1000mm×190mm & 190mm×90mm

## Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23  $\pm$  2  $^{\circ}$ C, and a relative humidity of 50  $\pm$  6  $^{\circ}$ C.

#### III. Test results

## 1) "Brandschacht" Test according to DIN 4102-15 &16

Exposed surface: The front face

Results of "Brandschacht" Test (part 1)								
Line		Unit	Test assemblies No.					
No.		Offic	Α	В	С	D		
1	Specimen fixings according to DIN 4102 part 15, table	-						
2	Max. flame height above lower sample edge;	cm	40					
3	Time 1)	min:s	0:05					
	Melting/burning through							
4	Time 1)	min:s	0:04					
	Back of specimen							
5	Flaming/glowing, Time 1)	min:s	0:04					
6	Discolouring, Time 1)	min:s	0:03					
	Burning droplets		NO					
7	Begin 1)	min:s	/					
	<u>Amount</u>		/					
8	Specimen material falling off in separate droplets		/					
9	Specimen material falling off continuously		/					

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overlead, available or request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification in and jurisdiction issues defined therein. Any holder of this document is advised that information contained bereon reflects the Company's findings at the time of its intervention only and within the limits of client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, forgery or falsification of the content appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, and the such extended to the full season content us at telephone (#6-755) 830?

No. 301, Sunight Road, 2 Block, Sunight Industry Zone, Anji County, Zhejiang Province, China 313300 t (多-572 5018825 f (多-572 5018825 www.spsgroup.com.cn 中国 - 浙江 - 安吉县阳光工业园二区阳光大道301号 邮编:313300 t (多-572 5018825 f (多-572 5018829 e sgs.china@sgs.com



Test Report Date: MAR.20, 2017 Page 3 of 6

Results of "Brandschacht" Test (part 2)									
Line		Unit	Test assemblies No.						
No.		01110	Α	В	С	D			
	Burning parts								
10	Begin 1)	min:s	0:53						
11	Parts of sample falling off separately		$\checkmark$						
12	Parts of sample falling off continuously								
13	Duration of continued combustion on mesh base (max.)	min:s	NO						
	Burner flame impairment by dripping/falling material		NO						
14	Time 1)	min:s	/						
	Premature ending of test		/						
15	End of burning at specimen 1)	min:s	/						
16	Time when test terminated (if applicable) 1)	min:s	/						
	Burning after end of test		NO						
17	Duration	min:s	/						
18	Number of specimens		/						
19	Front of specimen		/						
20	Back of specimen		/						
21	Height of flame	cm	/						
	Glowing after end of test		NO						
22	Duration	min:s	/						
23	Number of specimens		/						
24	Front of specimen		/						
25	Back of specimen		/						
26	Top half of specimen		/						
27	Bottom half of specimen		/						

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overlead, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-en-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions/Terms-en-Document.aspx</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's sindings at the time of its intervention only and within the limits of Cilent's instructions, if any. The Company's sole responsibility is to its Cilent and this document does not expense the expense of the company. Any unauthorized alternation, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this text export refer only to the sample(s) setted and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of texting / inspection report & certificate, please contact us at telephons: [36-755] 8307 1443, or amail: CN.Doccheck@ss.com

No. 301, Sunlight Road, 2 Blods, Sunlight Industry Zone, Anj County, Zhejang Province, China 313300 t (多-572) 5018825 f (多-572) 5018825 www.spsgroup.com.cn 中国 - 浙江 - 安古县阳光工业园二区阳光大道301号 邮编:313300 t (多-572) 5018825 f (多-572) 5018829 e sgs.china@sgs.com



Test Report Date: MAR.20, 2017 Page 4 of 6

Results of "Brandschacht" Test (part 3)												
Line		Unit	Test assemblies No.									
No.		Offit	Α		В		A B		С		D	
	Residual length											
	Single regulte	200	65	66								
20	28 Single results	cm	64	68								
29	Average of the single results	cm	65.8									
	Smoke temperature											
30	Max. of average	$^{\circ}\!\mathbb{C}$	141.2									
31	Time 1)	min:s	06:58									

Note: 1) time from start of testing

#### Class B1 materials:

If the residual length measured after the first test is 45cm or greater, further tests are not required.

## 2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Parameter		Lengthwise							
		2	3	4	5				
Whether or not flaming extinguished before reach the gauge mark(Yes/No)	Yes	Yes	Yes	Yes	Yes				
Whether or not flaming reach the measuring mark within 20 seconds(Yes/No)	No	No	No	No	No				
Time for the flame tip to reach the gauge mark(s)	No	No	No	No	No				
Time of flaming extinguished from fire application (s)	0	0	0	0	0				
Max. flame height (cm)	8	10	12	9	8				
Molten dripping(Yes/No)	No	No	No	No	No				
Smoke developments (visual impression)	Slight								

Note:

NA---Not applicable

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overlead, available or request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification in and jurisdiction issued effected therein. Any holder of this document is advised that information contained bereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, forgery of falsification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise so otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention To check the autherticity of testing / inspection report & certificate value telephone (#6-755) 8302

No. 301, Sunlight Road, 2 Blook, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (多572) 5018825 f (

<sup>\*</sup>Reduction in number of test (DIN 4102 Part 16, clause 5.2)



## Test Report Date: MAR.20, 2017 Page 5 of 6

#### DIN 4102-1:1998 Criteria for classification

- 1) All materials, except flooring, may be classed as **B1** materials if they meet the following requirements a) and b):
- a) The test using the 'Brandschacht' apparatus described in DIN 4102-15 (cf. subclause 6.1.3.1) shall be deemed passed if
- The mean value for the residual length (portion of specimen that has not burned or charred; cf. subclause
- 9.1 of DIN 4102-16) of each specimen is at least 15 cm and no individual values are lower than 0 cm,
- The mean effluent temperature does not exceed 200 °C in any test,
- The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.
- Pass DIN 4102-1: 1998 sub-clause 6.2.3 Ignitability Test if
   For each specimen, flaming doesn't reach the gage mark within 20s after flame application.
- 2) Materials may be classed as **B2** materials if they pass the ignitibility test specified in DIN 4102-1: 1998 subclause 6.2.5.

For each specimen, flaming doesn't reach the gage mark (150mm marks) within 20s after flame application.

3) Combustible materials which cannot be classed as B1 or B2 materials shall be classed as B3 materials.

#### **STATEMENTS**:

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overland, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document aspx. Attention is drawn to the limitation of liability, indemnification in and jurisdiction issues defined therein. Any holder of this document is advised that information contained bereon reflects the Company's findings at the time of its intervention only and within the limits of Cilent's instructions, if any. The Company's sole responsibility is to its Cilent and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, forgery or falsification of the content appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.


Attention: To check the authenticity of testing / Inspection report & certificate, please contact us at telephone: (86-755) 8302.

No. 301, Sunlight Road, 2 Blook, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (%-572) 501865 f (%-572) 501869 www.sgsgroup.com.cn 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (%-572) 501865 f (%-572) 501869 e sgs.china@sgs.com



## **Test Report**

## **Photo Appendix:**



Date: MAR.20, 2017

Page 6 of 6

SGS authenticate the photo on original report only

\*\*\*End of Report\*\*\*



Unless otherwise agreed in writing, this occument is issued by the Company subject to its General Conditions of Service printing overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx.and, for electronic format documents subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification in and jurisdiction issued elined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, forgery of falsification of the content appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention to check the authenticity of testing / inspection report a certificate, please contact us at telephone (au-ros) and
1443, or amail: CN.Doccheck@sgs.com

NN 315 Suidet Boot 7 Block Suidet Industry 7mg Ani Courte 7 Palace Province China 24:2000 + (64-57) 5/18005 + (64-57) 5/18005 www.spscrpun.com